



Making it Greener With Myrifilm®
Zero-VOC Coalescing Solvent



HIGH EFFICIENCY
ZERO VOC
LOW ODOR

"More for Less"

Myrifilm® is a bio-based, ultra-low odor, broad spectrum coalescing solvent. This high-efficiency coalescing solvent is zero-VOC, low odor, non-HAPS. Myrifilm® can be applied at substantially lower dosages compared to other coalescing solvents in some formulations and can be used in a wide range of coatings and adhesive formulations.

Applications

Myrifilm® can replace conventional coalescing solvents in a wide variety of waterborne coating systems, especially acrylic, styrene-acrylic and ethylene-vinyl acetate copolymers. Because it is zero-VOC, Myrifilm® allows the formulation flexibility that is needed to meet increasingly stringent environmental compliance regulations, without compromising performance.

Coatings formulated with Myrifilm® display good hardness, tint strength and scrub resistance, without the need for substantial reformulation. As with any product, the performance of Myrifilm® must be verified by the end user.

Myrifilm® Properties	
Purity	99.5 wt%
Moisture	< 500 ppm
Color	< 10 Pt-Co
Acid Number	0.01 mg KOH/g
Visual	Clear and free of suspended matter
Boiling Point	331.2°C
Odor	ultralow


Lower Dosage of Myrifilm® Yields Equal Performance

To compare coalescing solvents, Myrifilm® and Texanol™ were added to separate laboratory semi-gloss formulation samples. Myrifilm®'s efficiency was highlighted in producing identical film properties at half the concentration of Texanol™ with very low odor and zero-VOC based on ASTM D-6886.

Semi-Gloss Formulation	
Raw Material	Weight (lb.)
Grind	
Water	29.00
Tamol™ 731A	8.00
Delonic LF 80MOD	2.00
DEE FO® 3010A	0.50
Tafigel® PUR 80	17.00
Minex® 10	50.00
Attagel® 50	3.00
Myrifilm®/Texanol™	10.00/20.00
Disperse 30 minutes to a 6-7 grind	
Water	81.00
Letdown	
TiO2 Slurry	280.00
Water	80.00
Tafigel® PUR 80	12.00
Ropaque™ Ultra	60.00
Orgal* P85ORR	410.00
DEE FO® 3010A	1.50
Tafigel® PUR 61	10.00
Total	1054.0/1064.0
Equilibrate 24 hours	

Physical Properties	
Total VOC g/L	4
Density, lb/gal	10.54
Vol % Solids	36.84
Wt% Solids	48.79
PVC	34.09

*Orgal P850RR is an all acrylic resin from Organik Kimya with a Tg of 22 °C and a Minimum Film Formation Temperature (MFFT) of 18 °C, similar to BASF Acronal Optive® 220 or Dow Rhoplex™ AC 261.



Formulation Guide

Myrifilm® can be used identically as other coalescing solvents. However to optimize Myrifilm® usage and maximize properties, it is recommended to use the following procedure.



Surfactant

Myrifilm® works well with surfactants with high oil emulsifying property, such as alcohol ethoxylate, nonylphenol ethoxylate types.

Recommended Dosage Level

Determining an optimum dosage level of Myrifilm® is an iterative process. A good starting point is to try Myrifilm® at half the recommended level of Texanol™, and then conduct tests, such as low temperature coalescing (LTC). If it passes the LTC test and other properties are satisfactory, further reduction in the amount of coalescent can be tried next. If not, an increased level should be tested. In all tests, it is important to make sure that Myrifilm® is added prior to the resin and the required equilibration time is minimum 24h.

Performance Compared to Conventional Coalescing Solvents

Myrifilm® was evaluated in a typical semi-gloss formulation using Dow Rhoplex™ SG-30 all acrylic resin. The properties of both the paint and the finished film were evaluated. The coalescing solvents used for comparison were Texanol™ (Eastman), TXIB™ (Eastman), Optifilm™ 400 (Eastman) and dipropylene glycol monobutyl ether (DPnB from Dow). Using identical coalescent dosage, standard formulation procedure, 24 hour equilibration time, Myrifilm® performed equal or better than the other coalescing solvents in all tests.

Property	Property Comparison of Typical Coalescing Solvents				
	Myrifilm®	Texanol™	TXIB™	Optifilm™ 400	DPnB
KU Viscosity (Initial/24 h) (ASTM D-562)	87.9/104.2	90.7/107.8	99.3/115.7	94.7/112.3	83.8/95.4
Sag (ASTM D-4400)	10.7	10	11.3	10.7	7.3
Leveling (ASTM D-4062)	4	4	4	4	3.8
Contrast Ratio (Air-dry, 24h) (ASTM D-2805)	96.24	96.25	96.43	96.98	96.4
Gloss 20°/60°/85° (ASTM D-523)	44.4/74.4/97.9	39.8/75.3/97.8	39.8/75.1/97.6	45.5/78.0/98.2	37.4/73.3/96.2
Block Resistance (120 °F, 24h) (ASTM D-4946)	5	6	5.33	5.67	6
Scrub Resistance (2,400 cycles)	8	8	9	9	8
LTC (40 °F, 10 mil) (ASTM D-7306)	5	5	5	5	5
Tint Strength (Red) %TSUC	103.3	99.8	104.3	100.8	97.1
Tint Strength (Yellow) %TSUC	83.5	99.4	80.1	74.3	90.1
Tint Strength (Blue) %TSUC	101.4	100	105.8	99.7	80.5

Performance in Various Resin Types


In order to evaluate Myrifilm®'s performance in other resin systems, the same semi-gloss formulation was used. The resin was replaced as indicated in the following table, and low temperature coalescing (LTC) characteristics were evaluated based on ASTM D-7306, where 5 indicated no cracking and 0 indicated film chipping off completely. These results show that Myrifilm® is an effective coalescent in a broad range of typical resins used for both coatings and adhesives.

	Low Temperature Coalescing (10 mil/250 Micron Film)	Low Temperature Coalescing (5 mil/125 Micron Film)
Rhoplex™ SG-30 (Acrylic) with Myrifilm®	4	3
Rhoplex™ SG-30 (Acrylic) with Texanol™	3	1
Styrofan® ND 593 (Styrene/Butadiene) with Myrifilm®	5	4
Styrofan® ND 593 (Styrene/Butadiene) with Texanol™	5	5
Acronal® S504 (Acrylic) with Myrifilm®	5	5
Acronal® S504 (Acrylic) with Texanol™	5	5
Acronal® 296D (Styrene/Acrylic) with Myrifilm®	5	5
Acronal® 296D (Styrene/Acrylic) with Texanol™	5	5

Ultra-Low Odor Compared to Other Coalescing Solvents

A blind study was conducted to compare odors of commercial waterborne interior flat wall paint formulated with Myrifilm[®], Texanol[™] ester alcohol (Eastman), Optifilm[™] enhancer 400 (Eastman) and one with no coalescent as the control.

The paints were evaluated for their odor characteristic at three intervals under controlled ambient conditions. The test results data from the average odor response of twenty panelists illustrated a much lower odor characteristic in the paint containing Myrifilm[®]. In addition the residual odor of the paints after air dry at room temperature for 1 and 3 hours also indicated that the paint containing Myrifilm[®] has a very low odor comparable to paint containing no coalescing solvent and much lower than the paint containing Texanol[™] ester alcohol or Optifilm[™] enhancer 400.



Safety and Regulatory

Myrifilm[®] is listed on the U.S. TSCA inventory, the Canadian DSL, the Korean ECL, the Australian AICS and is registered under REACH (01-2119985662-25-0000).

When using this product, the information and advice given in the Material Safety Data Sheet should be observed. Normal precautions for the handling of chemicals, including wearing proper personal protective equipment, should be followed at all times. The Material Safety Data Sheet is available on request.

Handling and Storage

Store in a tightly closed container in a cool, well-ventilated area away from sources of heat or ignition.

Packaging

Samples are available in 1-liter or 1-gallon bottles. Product is available in steel drums, totes or in bulk.

SAMPLES AVAILABLE! Order today by calling
+ 1 855.MYRIANT or visiting www.myriant.com.

NOT ALL CHEMICALS ARE CREATED EQUAL[®]



CORPORATE OFFICE

42 Cummings Park
Woburn MA 01801 USA
+1 781-569-6250

To order samples, contact productinfo@myriant.com
Phone: +1 855.MYRIANT | www.myriant.com

For more information, scan the QR Code!

